

Chavant Clay Datenübersicht

	Härtegrad (Skala 1 - 10)	Spezifisches Gewicht (g/cm³)	Arbeits- temperatur (°C)	Erweichungs- temperatur (°C)	Veflüssigungs- temperatur (°C)
Industrial Design Clay (Industrie Clay)					
Autostyle soft	5	1,05	55	55 - 60	80 - 83 *
Autostyle medium	7	1,05	55	55 - 60	80 - 83 *
Autostyle hard	9	1,05	55	55 - 60	80 - 83 *
Y2	10	1,05	57	43 - 46	80 - 83 *
* für ca. 2-3 Stunden.					
Fine Arts Clay (Künstler Clay)					
DaVinci soft	1	1,56	20 - 41	n/a	n/a
DaVinci firm	2	1,56	20 - 41	n/a	n/a
Professional Plastiline	3	1,47	20 - 41	n/a	n/a
NSP soft	4	1,55	20 - 41	40	80 - 90
NSP medium	7	1,59	20 - 41	40	80 - 90
NSP hard	9	1,76	20 - 41	40	80 - 90
Le Beau Touche	4	1,48	20 - 32	n/a	n/a
Le Beau Touche HM	5	1,48	20 - 46	n/a	n/a